

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 September 2002 (12.09.2002)

PCT

(10) International Publication Number
WO 02/070620 A1

(51) International Patent Classification⁷: C09J 4/06,
175/16, C08F 290/06

(21) International Application Number: PCT/IB02/00865

(22) International Filing Date: 7 March 2002 (07.03.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01105349.3 8 March 2001 (08.03.2001) EP

(71) Applicant (for all designated States except US): SIKA AG,
VORM. KASPAR WINKLER & CO. [CH/CH]; Tüffen-
wies 16-22, CH-8048 Zürich (CH).

(72) Inventors; and

(75) Inventors/Applicants (for US only): DE COOMAN, Ria
[BE/CH]; Sonnegut, CH-6331 Hünenberg (CH). MEYER,
Werner, R. [CH/CH]; Binderstrasse 62, CH-8702 Zollikon
(CH).

(74) Agent: E. BLUM & CO.; Vorderberg 11, CH-8044 Zürich
(CH).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: EASY TO MANUFACTURE METH(ACRYLIC) ADHESIVE COMPOSITIONS

(57) Abstract: Described are adhesive compositions comprising: (i) at least one reactive monomer (A) selected from ethylenically unsaturated carboxylic acid derivatives and mixtures of such derivatives, said one or more derivatives preferably being one or more esters, (ii) at least one liquid elastomer in a molar weight range of 1000 - 9000 which is functionalized with ethylenically unsaturated groups (B), (iii) at least one impact modifier (C) that is a core shell polymer that does not dissolve but swells in the monomer (i), and (iv) at least one free radical initiator and at least one catalyst, whereby the amount of B referred to the total amount of A+B is 15 to 60 % by weight, and whereby optionally either said initiator, or said catalyst is present separately, in a further component or paste, respectively. Preferably the amount of C referred to the total amount of A+B+C = 5 - 30 % by weight.



WO 02/070620 A1

**Easy to Manufacture Meth(acrylic) Adhesive
Compositions**

5 Cross References to Related Applications

 This application claims the priority of
European patent application no. 01 105 349.3, filed March
8, 2001, the disclosure of which is incorporated herein
10 by reference in its entirety.

Technical Field

 The present invention relates to easy to
15 manufacture adhesive compositions based on meth(acrylic)
systems comprising a liquid elastomer and an impact
modifier.

20 Background Art

 Methacrylic adhesives combine a number of
advantageous properties that make them the ideal solution
for many bonding applications. Compared to adhesives
based on other chemistries like polyurethanes or epoxies
25 they allow for a relatively long open time with a
subsequent fast build-up of strength. Two component
methacrylic adhesives reach handling strength within
minutes after mixing, and over 80% of the final strength
is usually reached within less than an hour. Furthermore,
30 they usually show an excellent adhesion on a wide range
of substrates from metals to plastics, like ABS,
polyesters, etc. often without pre-treatment. One major
requirement an adhesive system needs to fulfill is the
durability of the bond. In many applications the long-
35 term performance is significantly increased by the
flexibility and the impact resistance of the adhesive.
While the two-component meth(acrylic) adhesives of the

first generation, formulated with methyl methacrylate, inert fillers e.g. calcium carbonate, catalysts and peroxide initiators show brittle behavior, many efforts have been made in the past to improve flexibility and impact resistance of these systems.

One of said efforts to improve flexibility and impact resistance led to the addition of solid non-reactive elastomers that are dissolved in the meth(acrylic) monomers. Such compositions are called rubber-toughened adhesive compositions. The elastomers are solids at room temperature, and commercially available as large particles or granulates.

This approach is described in several patent documents, such as: US 3,890,407, US 4,106,971, US 4,263,419, US 3,725,504, US 4,200,480, US 3,994,764, EP 0 641 846. The disadvantage of such formulations is that they can only be mixed homogeneously after extremely long dissolving times, or with special equipment like extruders or kneaders due to the high viscosity of the polymer. Moreover, this type of compositions suffers from the limitation that the monomer, or the monomer mixture, must be chosen such that the non-reactive thermoplastic polymer is soluble therein. Practically, methyl methacrylate is the only monomer with high dissolving properties, and thus the only monomer that allows a polymer-in-monomer composition with up to 30% polymer content. Such low molar mass monomers, like methyl methacrylate, have a strong odor and are highly flammable. Polymer-in-monomer compositions resulting from this approach have a rubbery, stringy consistency and a high viscosity that makes their handling difficult. Due to the high viscosity of the mixture, only a limited amount of fillers can be used making the formulation expensive. A high viscosity is also limiting the adhesion of the formulation, as it limits the wetting of the substrate. Finally, the impact resistance, especially at low temperatures, is low.

Further known are adhesives with multi phase morphology (with core-shell polymers). It is known that composites with a dispersed rubbery phase with a low glass transition temperature have a superior impact resistance. The multi phase morphology can be obtained with core-shell polymers. Core-shell polymers consist of cross-linked acrylic based or butadiene based elastomeric core phase polymers which are grafted onto an outermost rigid thermoplastic polymer. Such core-shell polymers are primarily used as impact modifiers in certain polymer systems like PVC. Because of the cross-linked core such polymers do not dissolve but only swell in the monomers. Such core-shell polymers are e.g. described in US 3,985,703 and US 6,985,704, and adhesive composition with multi phase morphology using core-shell polymers are described in EP 0 087 304.

This approach, however suffers from the limitations that, although these compositions have a high impact-resistance, their elongation at break is low.

Another known approach is the addition of liquid, low- molar mass elastomers that mix easily with the monomers to form homogeneous liquids. A number of patent documents describe such approach to increase the flexibility of the systems, namely US 4,769,419; US 4,331,765; EP 0,561,352 disclosing mixtures of monomer and liquid rubber.

DE 2,610,423; US 4,439,600; EP 0,640,672; DE 2,319,637; US 4,223,115 disclose mixtures of monomer and acrylic functionalised polyurethane. In US 4,223,115 the formulation optionally contains a dissolved solid elastomer, e.g. NBR (nitrile-butadiene-rubber), polychloroprene.

The limitation of this approach is that all these compositions lack impact resistance, especially at low temperatures.

Also already known are combinations of solid elastomers, core-shell polymers and monomers.

Combinations of solid elastomers and core-shell polymers and monomers are described in US 4,942,201 and US 5,206,288. The dissolved elastomer provides the adhesive with flexibility and the dispersed core-shell graft co-
5 polymer insures a high impact resistance also at low temperatures. The ratios of the three components found in the state of the art are

monomers: solid elastomers: core-shell
polymers = A:B:C

10 B in A+B = 5% - 20% or 10% - 35%, and - in
another document -

C in A+B+C = 10% - 30%.

Such compositions show the same limitations
15 as solids in monomers with the exception that they provide improved impact resistance over solid elastomers alone.

All these systems of the state of the art have limited properties with regard to flexibility and/or
20 impact resistance, or they are difficult to manufacture.

Disclosure of the Invention

25 Hence, it is a general object of the invention to provide an adhesive composition with good flexibility and impact resistance that is furthermore easy to manufacture.

It has now surprisingly been found that
30 adhesive compositions with very good flexibility and impact resistance are obtained if they comprise

(i) at least one reactive monomer (A)
selected from ethylenically unsaturated carboxylic acid derivatives and mixtures of such derivatives, said one or
35 more derivatives preferably being one or more esters,

(ii) at least one liquid elastomer in a molar weight range of 1000 - 9000 which is functionalized with ethylenically unsaturated groups (B),

(iii) at least one impact modifier (C) that
5 is a core shell polymer that does not dissolve but swells in the monomer (i), and

(iv) at least one free radical initiator and at least one catalyst,

whereby the amount of B based on the total
10 weight of A + B is 15 to 60 % by weight, and

whereby optionally either said initiator, or said catalyst is present separately, in a further component or paste, respectively.

Preferably C is present based on the total
15 weight of A+B+C in an amount of 5 to 30 % by weight.

Modes for Carrying Out the Invention

As already mentioned above, the inventive
20 adhesive compositions with very good flexibility and impact resistance are obtained if they comprise

(i) at least one reactive monomer (A) selected from ethylenically unsaturated carboxylic acid derivatives and mixtures of such derivatives, said one or
25 more derivatives preferably being one or more esters,

(ii) at least one liquid elastomer in a molar weight range of 1000 - 9000 which is functionalized with ethylenically unsaturated groups (B),

(iii) at least one impact modifier (C) that
30 is a core shell polymer that does not dissolve but swells in the monomer(i), and

(iv) at least one free radical initiator and at least one catalyst,

whereby the amount of B based on the total
35 weight of A+B is 15 to 60 % by weight, and

whereby optionally either said initiator, or said catalyst is present separately, in a further component or paste, respectively.

Preferably the core shell polymer C is
5 present based on the total weight of A+B+C in an amount of 5 to 30 % by weight.

Optionally the composition can further comprise at least one adhesion promotor like (meth)acrylic acids, (meth)acrylic phosphate esters,
10 silanes such as 3-mercaptopropyltrimethoxysilane, (3-methacryloyloxypropyl)trimethoxysilane and 3-glycidyloxypropyltrimethoxysilane or the respective triethoxysilanes, or mixtures of said silanes, and/or Zn di(meth)acrylates.

15 In a much preferred embodiment, the adhesive composition of the present invention comprises the components A, B, and C in the following amounts:

B based on the total weight of A+ B in an amount of 15 - 40 % by weight, and

20 C based on the total weight of A+B+C in an amount of 10 to 25 % by weight.

The reactive monomers (A), preferably are esters, in particular esters that have no groups leading to hydrogen bond formation such as free carboxylate or
25 carboxylic acid groups. Preferred esters are (meth)acrylic esters, in particular linear or branched or cyclic C₁-C₆-alkyl esters or heterocyclic or aromatic esters. Much preferred esters are methylmethacrylate (MMA), tetrahydrofurfurylmethacrylate (THFMA),
30 cyclohexylmethacrylate (CHMA), and cyclic trimethylolpropane formal acrylate (CTFA), isobornylmethacrylate (IBMA), benzylmethacrylate (BMA), dicyclopentadienyloxyethylmethacrylate (DCPOEMA), t-butylmethacrylate (tBMA), isobornylacrylate (IBH),
35 dihydrodicyclopentadienylacrylat (DHDCPA).

Examples for free radical initiators are organic peroxides, in particular benzoylperoxide, and

examples for catalysts are tertiary amines and/or salts and/or complexes of transition metals. Examples for tertiary amines are N,N-dimethylaniline, N,N-dimethyl-p-toluidine, N,N-diethylaniline, N,N-diethyltoluidine, N,N-bis(2-hydroxyethyl)-p-toluidine, N-ethoxylated p-toluidine, N-alkylmorpholine or mixtures thereof, and examples for the salts and complexes of transition metals are salts and complexes of cobalt, nickel and/or copper.

Preferred adhesive composition of the present invention are compositions wherein the reactive monomer comprises at least 50 % of (meth)acrylic monomer, and whereby at least 50% of said (meth)acrylic monomer is tetrahydrofurfuryl methacrylate or methyl methacrylate or mixture thereof. In a much preferred embodiment, at least 50 % of the reactive monomer(s) is tetrahydrofurfuryl methacrylate or methyl methacrylate or mixture thereof.

It is also preferred that the homo- or copolymers resulting from said reactive monomers A have a glass transition temperature of from about 40°C to about 140°C.

With regard to the liquid elastomer (B), said elastomer is preferably chosen from the group consisting of

- (meth)acrylic functionalized butadiene, isoprene based polymers or block-copolymers, and
- PU-(meth)acrylate obtainable through the syntheses of a polyethylene polyol or polypropylene polyol, a diisocyanate and a hydroxy functionalized ethylenically unsaturated monomer, and
- mixtures thereof.

A preferred PU (meth)acrylate is obtainable through a synthesis using polyols with low unsaturation and narrow molar weight distribution as obtainable through double metal cyanide complex catalysis (Acclaim polyols). As well preferred as liquid elastomers are (meth)acrylic terminated butadiene acrylonitrile block copolymers.

The impact modifier (C) is a core shell polymer which does not dissolve, but swells in the monomer. Suitable core-shell polymers contain a cross-linked acrylic or butadiene based elastomeric core phase polymer which is grafted onto a rigid thermoplastic shell phase polymer.

The compositions of the present invention can comprise further components well known to the skilled person such as preferably also at least one organic or inorganic filler or thixotropic agent. The compositions can also comprise further substances, such as stabilizers, additives, toughening agents, adhesion promoters, defoaming agents, thickeners, plasticizers, wetting agents, wax compounds, cross-linking agents, inhibitors etc. Such additional substances are known to the skilled person. Examples for inhibitors are e.g. hydroquinone, methylhydroquinone, t-butyl-p-cresol and for thixotropic agents e.g. Aerosil.

The compositions of the present invention usually and preferably are designed for aerobic use, e.g. with the preferred initiators/catalysts described above.

The compositions of the present invention can be easily manufactured in a short time. To optimize the consistency of the paste it has proved to be advantageous to usually start with only part, usually about half of the amount of reactive monomer A and to add the second part at a later stage.

A usual procedure is as follows: A first part (or if viscosity allows it all) of reactive monomer A, the liquid elastomer B and catalyst and/or initiator D are mixed under heating and stirring until a homogenous mass is obtained (at a temperature of about 60°C for about 30 minutes). Then the whole amount of impact modifier C is added at once, and the mixture is stirred for approx. another 30 minutes. Finally, the second part of reactive monomer A is added and the composition is stirred for another about 30 minutes under vacuum.

Usually either the catalyst or the initiator D are provided in a separate component unless at least one of them is present in a non-reactive form so that it has first to be activated, e.g. by heating.

5 The invention is now further described by means of examples. Said examples, however, shall not limit the scope of the present invention in any way.

10 **Examples**

Preparation of compositions

 The components used in the examples are identified as:

15

MMA	Methyl methacrylate
THFMA	Tetrahydrofurfuryl methacrylate
CHMA	Cyclohexyl methacrylate
CN 965	aliphatic polyurethane-acrylate
20 Hycar VTBNX	with a MW 5600 from Cray Valley
1300 X33	acrylic functionalized butadiene-
	acrylo nitrile blockcopolymer from
	BFGoodrich
25 Paraloid EXL 2600	core shell polymer from Rohm and Haas
p-Toluidine	N,N-bis(2-hydroxyethyl)-p-toluidine
BPO Paste	a paste of 40 % benzoyl peroxide in
30	phthalate plasticizer

 The components used to formulate the adhesive compositions of Examples 1 to 7 and their amounts are listed in Table 1.

35

The composition was produced as follows:

Half the amount of reactive monomer A, the liquid elastomer B and catalyst D are added to a vessel equipped with a stirrer, a heating device and a vacuum device. The heating is turned on, and the mixture is stirred for about 30 minutes at 60°C until a homogenous mass was obtained. Then, the heating is turned off, the whole amount of the impact modifier C is added at once, and the mixture is stirred for approx. 30 minutes. Finally, the remaining amount of reactive monomer A is added and the composition stirred for about 30 minutes under vacuum.

For 1 kg of the composition of e.g. Example 2 the above described procedure was applied as follows:

265 g of tetrahydrofurfuryl methacrylate are added together with 260 g of Hycar and 10 g of p-toluidine into a 1 kg lab dissolver equipped with an anchor stirrer and a heating and vacuum device. The heating is turned on and the mixture is stirred for about 30 minutes at 60°C until a homogenous mass is obtained. Then the heating is turned off, 200 g of Paraloid EXL 2600 are added at once, and the mixture is stirred for approx. 30 minutes. Finally, another 265 g of tetrahydrofurfuryl methacrylate are added and stirred for about 30 minutes under vacuum.

The adhesives were cured by adding 4 % of the BPO paste.

30

The test results obtained for the cured adhesives are also listed in Table 1.

The adhesives were tested as follows:

35

Test procedures:**Tensile strength and Elongation (DIN 53504)**

The adhesive was cured to form a sheet of
 5 approximately 2.5 mm thickness from which tensile test
 dumbbells were cut. The stress-strain tests were
 performed using a rate of 200 mm per minute for
 measurements at room temperature.

10 **Impact Test or Charpy Test (DIN 53453)**

The impact strength of the adhesive was
 tested using adhesive bars of 11.8 cm length, 12 cm width
 and 9.5 cm height. The impact strength was measured at
 the indicated temperature with a pendulum of 15 kg

15

Table 1

	<i>Ex 1</i>	<i>Ex 2</i>	<i>Ex 3</i>	<i>Ex 4</i>	<i>Ex 5</i>	<i>Ex 6</i>	<i>Ex 7</i>	<i>Designation</i>
MMA	57			43	70		70	A
THFMA		53	18			80		
CHMA			41					
EHA	0		7					
CN 965	18			43	7			B
Hycar VTB NX 1300 X33		26	20			19		
Paraloid EXL 2600	23	20	14	13	22		29	C
p-Toluidine	1	1	1	1	1	1	1	D
%B/A+B	24	33	23	50	9	19	0	
TS [Mpa]	18	9	15	11	34	15	21	
EaB [%]	135	210	155	219	19	140	28	
Impact at -20°C [mmJ/mm2]	35	40	25	30	25	<1	<5	

Examples 1 to 4 are compositions which provide adhesives with a high elongation and resistance to low temperatures. Example 5 is made by using a too low amount of liquid elastomer which results in an adhesive with a good low temperature impact resistance, but with a too low elongation. In example 6, a formulation is represented which does not contain any core-shell polymer. Although the elongation is high, the impact resistance of the material at low temperatures is low. Example 7, which is a composition containing only core shell polymer and no liquid elastomer, has not only a low elongation but also a reduced impact resistance. As this formulation does not contain any liquid elastomer (compared with example 5 which contains a low amount of elastomer), the interface between polymer matrix and the impact modifier is not coherent enough to transfer the energy from the matrix onto the impact modifier.

While there are shown and described presently preferred embodiments of the invention, it is to be distinctly understood that the invention is not limited thereto but may be otherwise variously embodied and practiced within the scope of the following claims.

Claims

1. An adhesive compositions comprising
 - (i) at least one reactive monomer (A)
5 selected from ethylenically unsaturated carboxylic acid derivatives and mixtures of such derivatives,
 - (ii) at least one liquid elastomer in a molar weight range of 1000 - 9000 which is functionalized with ethylenically unsaturated groups (B),
 - 10 (iii) at least one impact modifier (C) that is a core shell polymer that does not dissolve but swells in the monomer (i), and
 - (iv) at least one free radical initiator and at least one catalyst,
 - 15 whereby the amount of B based on the total mount of A+B is 15 to 60 % by weight, and
whereby optionally either said initiator, or said catalyst is present separately, in a further component or paste, respectively.
- 20 2. The adhesive composition of claim 1 wherein the amount of B based on the total amount of A+B is 15 - 40 % by weight.
3. The adhesive composition of claim 1 or 2 wherein the amount of C based on the total amount of
25 A+B+C is 5 - 30 % by weight.
4. The adhesive composition of claim 1 or 2 wherein the amount of C based on the total amount of A+B+C is 10 - 25 % by weight.
5. The adhesive composition of anyone of the
30 preceding claims, wherein said at least one ethylenically unsaturated carboxylic acid derivative is an ester or a mixture of esters.
6. The adhesive composition of anyone of the preceding claims, wherein the reactive monomer is a
35 (meth)acrylic monomer.
7. The adhesive composition of anyone of the preceding claims, wherein the reactive monomer comprises

at least 50% of tetrahydrofurfuryl methacrylate or methyl methacrylate or mixtures thereof.

8. The adhesive composition of anyone of the preceding claims, wherein the glass transition
5 temperature of the homo- or copolymer resulting from said reactive monomers A is between 40°C and 140°C.

9. The adhesive composition of anyone of the preceding claims, wherein the liquid elastomer (B) is chosen from the group consisting of

- 10 - (meth)acrylic functionalized butadiene,
isoprene based polymers or block-copolymers, and
 - PU-(meth)acrylate obtainable through the
syntheses of a polyethylene polyol or polypropylene
polyol, a diisocyanate and a hydroxy functionalized
15 ethylenically unsaturated monomer, and
 - mixtures thereof.

10. The adhesive composition of claim 9,
wherein the PU (meth)acrylate is obtainable through a
synthesis using polyols with low unsaturation and narrow
20 molar weight distribution as obtainable through double
metal cyanide complex catalysis.

11. The adhesive composition of claim 9 or
10; wherein the liquid elastomer is a (meth)acrylic
terminated butadiene acrylonitrile blockcopolymer.

25 12. The adhesive composition of anyone of the
preceding claims wherein the initiators is an organic
peroxide, in particular benzoylperoxide, and the catalyst
is selected from the group consisting of tertiary amines,
and salts of transition metals and complexes of
30 transition metals, in particular the catalyst is selected
from the group consisting of N,N-dimethylaniline, N,N-
dimethyl-p-toluidine, N,N-diethylaniline, N,N-diethyl-
toluidine, N,N-bis(2-hydroxyethyl)-p-toluidine, N-
ethoxylated p-toluidine, N-alkylmorpholine or mixtures
35 thereof, or from the group consisting of salts and
complexes of cobalt, nickel and copper and mixtures
thereof.

13. The adhesive composition of anyone of the preceding claims which contains an adhesion improving agent, in particular an adhesion improving agent selected from the group consisting of (meth)acrylic acids,
5 (meth)acrylic phosphate esters, silanes such as 3-mercaptopropyltrimethoxysilane, (3-methacryloyloxypropyl)trimethoxysilane and 3-glycidyloxypropyltrimethoxysilane or the respective triethoxysilanes, or mixtures of said silanes, and/or Zn di(meth)acrylates.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 02/00865

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09J4/06 C09J175/16 C08F290/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 439 600 A (MORAN JR JAMES P) 27 March 1984 (1984-03-27) column 11, line 38-42	1-6, 8-10, 12, 13
A	WO 00 77109 A (LORD CORP) 21 December 2000 (2000-12-21) examples	1-9, 12, 13
A	EP 1 013 735 A (THREE BOND CO LTD) 28 June 2000 (2000-06-28) claim 1; examples	1-10, 13
A	WO 00 73397 A (LORD CORP) 7 December 2000 (2000-12-07) the whole document	1-6, 9, 11-13

	---/---	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

8 July 2002

Date of mailing of the international search report

17/07/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Meulemans, R

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 02/00865

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 710 235 A (ABBAY KIRK JOSEPH ET AL) 20 January 1998 (1998-01-20) column 8, line 51-54; claims 1,2,11 -----	1
A	WO 95 25760 A (DSM NV) 28 September 1995 (1995-09-28) claim 1 -----	1
A	US 5 994 464 A (FUJII TATSUO ET AL) 30 November 1999 (1999-11-30) claim 1 -----	1
A	US 4 942 201 A (BRIGGS PAUL C ET AL) 17 July 1990 (1990-07-17) claim 1 -----	1
A	US 5 206 288 A (BRIGGS PAUL C ET AL) 27 April 1993 (1993-04-27) claim 1 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/IB 02/00865

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4439600	A	27-03-1984	AU 2838484 A	06-12-1984
			CA 1216982 A1	20-01-1987
			EP 0130680 A2	09-01-1985
			NO 842212 A	04-12-1984
			ZA 8403797 A	24-12-1984
WO 0077109	A	21-12-2000	US 2001051701 A1	13-12-2001
			AU 5327300 A	02-01-2001
			BR 0011465 A	19-03-2002
			EP 1190011 A2	27-03-2002
			WO 0077109 A2	21-12-2000
EP 1013735	A	28-06-2000	JP 10237420 A	08-09-1998
			BR 9812422 A	26-09-2000
			DE 69802000 D1	15-11-2001
			DE 69802000 T2	06-06-2002
			EP 1013735 A1	28-06-2000
			US 6232431 B1	15-05-2001
			CN 1248281 T	22-03-2000
			ES 2162416 T3	16-12-2001
			WO 9837161 A1	27-08-1998
WO 0073397	A	07-12-2000	US 6225408 B1	01-05-2001
			AU 5037800 A	18-12-2000
			WO 0073397 A1	07-12-2000
US 5710235	A	20-01-1998	AU 1129697 A	03-07-1997
			CN 1202908 A	23-12-1998
			DE 69620013 D1	25-04-2002
			EP 0866809 A1	30-09-1998
			JP 2000502136 T	22-02-2000
			WO 9721735 A1	19-06-1997
WO 9525760	A	28-09-1995	AU 1962995 A	09-10-1995
			WO 9525760 A1	28-09-1995
			US 6355599 B1	12-03-2002
			US 6021338 A	01-02-2000
US 5994464	A	30-11-1999	JP 8259899 A	08-10-1996
			CN 1138614 A , B	25-12-1996
US 4942201	A	17-07-1990	AU 3904589 A	01-03-1990
			CA 1331495 A1	16-08-1994
			DE 68913867 D1	21-04-1994
			EP 0357304 A2	07-03-1990
			ES 2062016 T3	16-12-1994
			IE 80687 B1	02-12-1998
			JP 2167377 A	27-06-1990
			JP 2745425 B2	28-04-1998
			KR 9304702 B1	03-06-1993
			US 5206288 A	27-04-1993
			US 5112691 A	12-05-1992
US 5206288	A	27-04-1993	US 4942201 A	17-07-1990
			AU 636770 B2	06-05-1993
			AU 7941391 A	09-01-1992
			BR 9102646 A	21-01-1992
			CA 2044861 A1	06-01-1992

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 02/00865

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5206288 A		IE 912336 A1	15-01-1992
		JP 4226579 A	17-08-1992
		AU 3904589 A	01-03-1990
		CA 1331495 A1	16-08-1994
		DE 68913867 D1	21-04-1994
		EP 0357304 A2	07-03-1990
		ES 2062016 T3	16-12-1994
		IE 80687 B1	02-12-1998
		JP 2167377 A	27-06-1990
		JP 2745425 B2	28-04-1998
		KR 9304702 B1	03-06-1993
		US 5112691 A	12-05-1992